

Clarifoil Acetate Film

Bulletin #P-14

- A smooth transparent material for use in electrical applications requiring high dielectric strength, abrasion resistance and water and moisture repellency. An Acetate wrapped tube can be wound, cut and packaged at the winding machine
- Clarifoil Acetate Film has the following physical properties:

| Typical physical properties of 'Clarifoil' measured at 23°C and 50% RH. | UP to 100 microns of thickness | 125 – 380 micros |
|--|------------------------------------|--------------------------------------|
| Specific Gravity | L31 | L30 |
| Tensile near distortion temperature (ASTM D1637) | 140°C | 123°C |
| Heat shrinkage % linear 100° for 4 hours (ASTM D1204) | 1.1% maximum | 1.1% maximum |
| Water vapor permeability g/m ² / 24 hours for 25 microns of thickness. 0-100 RH gradient. | 420 | 520 |
| Tensile yield strength, Kgs/cm ² (ASTM D882) | 510 | 475 |
| Tensile strength at break, Kgs/cm ² (ASTM D882) | 700 | 650 |
| Elongation at break, % (ASTM D882) | 20 | 30 |
| Elastic modulus in tension, Kgs/cm ² (ASTM D882) | 2.8 x 10 ⁴ | 2.3 x 10 ⁴ |
| Mullens bursting strength (ASTM D774) | 6 kg / cm ² (50 micron) | 24 kg / cm ² (250 micron) |
| Elmendorff tear strength (ASTM D689) | 10 gms (50 micron) | 300 gms (250 micron) |
| Volume Resistivity, ohms/ cm ² | 6.5 x 10 ¹² | 6 x 10 ¹² |
| Dielectric constant at 100 KHz | 4.9 | 4.2 |
| Loss factor at 100 KHz | .044 | .041 |
| Dielectric strength at Volts / mil (B.S. 2782) | 2100 | 2200 |
| Surface energy, dyn / cm (ASTM 2578-67) | 47 - 52 | 44 - 47 |

Paramount Tube
1430 Progress Rd
Fort Wayne, IN 46808
800-887-1475
Web: www.paramounttube.com
Email: info@paramounttube.com

Note: This material property information is the best currently available on the subject. The data should be viewed as a general guide to tube and material properties, not a performance guarantee. The customer should examine the suitability of the finished product for individual applications.